

**Abstract**

A setting and curing accelerator for hydraulic binders comprises:  $\text{Al}_2(\text{SO}_4)_3$  aluminum sulfate,  $\text{Al}(\text{OH})_3$  aluminum hydroxide and mineral acid in aqueous solution.

The setting and curing accelerator preferably comprises:

- 10-50% of  $\text{Al}_2(\text{SO}_4)_3$  aluminum sulfate,
  - 5-30% of  $\text{Al}(\text{OH})_3$  aluminum hydroxide,
  - 10 - 0.5-10% of a mineral acid
- in aqueous solution.